

PULSAFEEDER STANDARD PAINT SPECIFICATIONS

Description: Lime green water based epoxy manufactured by Mansfield Paint Company.

Properties of Dry Film:

<u>Description</u>	<u>Value</u>	<u>Test Method and References</u>
Gloss	90-95	ASTM D523-89 60° Geometry
% Adhesion	100	ASTM D3359, Test Method B
Pencil Hardness-HB	HB - F+ @ 16 Hours Cure	ASTM D3363
Flexibility	Pass C"	ASTM, D522, Method B
Impact Resistance	160"/# Direct 100"/# Reverse	ASTM D2794-93 e" Indenter
Abrasion Resistance	Good	
Outdoor Exposure	Excellent for Class	Normal gloss loss & chalking
5% Salt Spray Resist.	240+ hours + DTM 1.2 DFT	ASTM B117
Heat Resistance	250° F Continuous 350° F Intermitent	ASTM D2485