

**PULSAube TECHNICAL DATA**

**PULSAube #5**

**Service Range**

For adverse temperature conditions, service range -40°F to 400°F

**Nearest Commercial Equivalent**

Mobil - Mobil SHC 624

**Typical Characteristics**

API Gravity	-	34
Viscosity SSU @ 100°F	-	150
Viscosity SSU @ 210°F	-	46
Viscosity Index	-	135
Pour Point	-	-65°F
Four Ball Wear Test		
1800 RPM, 40 KG Load, 200°F, 1 Hr	-	.40 MM Scar Diameter
Timken OK Load	-	60 - 70 Lb.
Rust Test (ASTM D-665)	-	Pass
Demulsibility Test (ASTM D-2711)	-	Pass
Oxidation Test (ASTM D-2893)	-	Pass