



SECTION:
PAGE:
EFFECTIVE:
SUPERSEDES:

ORDER SERVICES
72
02/13/04
03/03/97

PULSAFEEDER ALTERNATE TOP COAT SPECIFICATIONS

Description: Lime green solvent-based aliphatic urethane manufactured by Devoe High Performance Coatings.

Properties of Dry Film:

<u>Description</u>	<u>Value</u>	<u>Test Method and References</u>
Minimum DFT	1.5 mils	DeFelsko Coating Thickness Gauge
Surface Finish	Gloss (90 units at 60°)	
Adhesion	Excellent	ASTM D 3359-02
Hardness	4H @ 7 days cure	ASTM D 3363
Abrasion Resistance	Excellent	ASTM D 4060
Outdoor Exposure	Excellent	
Salt Spray Resistance	Excellent	ASTM B 117