



SECTION:  
PAGE:  
EFFECTIVE:  
SUPERSEDES:

ORDER SERVICES  
71  
02/13/04  
03/03/97

## PULSAFEEDER STANDARD TOP COAT SPECIFICATIONS

**Description:** Lime green solvent-based two-part epoxy manufactured by Devoe High Performance Coatings.

### Properties of Dry Film:

<u>Description</u>	<u>Value</u>	<u>Test Method and References</u>
Minimum DFT	1.5 mils	DeFelsko Coating Thickness Gauge
Surface Finish	Semi-Gloss	
Adhesion	Excellent	ASTM D 3359-02
Hardness	3H @ 7 days cure	ASTM D 3363
Abrasion Resistance	Excellent	ASTM D 4060
Outdoor Exposure	Excellent	Loss of gloss, same protection
Salt Spray Resist.	Excellent	ASTM B 117